

9302 GARFIELD AVE • SOUTH GATE, CA 90280-3805



PRODUCT SPECIFICATIONS

PRODUCT: LIQUID ASPHALT SLOW-CURING

GRADE: SC-800

DATE: 12/10/2015

MEETS SPECIFICATIONS: ASTM 2026

TESTS	ASTM METHOD	AASHTO METHOD	SPECS.
Viscosity, 135°C(275°F), cSt	D2170	T201	800-1600
Flashpoint, C.O.C., °F	D92	T48	220 Min
API Gravity, 60°F	D287		
Density, 60°F, Lbs/Gallon	D287		
Water, vol. %	D95	T55	0.5 Max
Solubility in Trichloroethylene %	D2042	T44	99.0 Min
Distillation Test:	D402	T78	
Total Distillate to 500 °F,%	D402	T78	0.5 Max
Total Distillate to 680 °F,%	D402	T78	2-12
Viscosity of Residue 60°C(140°F), Cst	D2170	T201	2000-16000
Asphalt ResidueTest	D243	T56	
Residue of 100 Penetration, %	D5	T49	70Min
Ductility of 100 pen. Res., cm	D113	T51	100Min

AVAILABILITY: Readily available

DOT SHIPPING NAME: NA1999,Hot Asphalt,Cutback, 3,III

DOT PLACARD:Class 3,1999