



PRODUCT SPECIFICATIONS

PRODUCT: ROOFING ASPHALT

GRADE: 114 WINDSEAL

DATE: 12/10/2015

MEETS SPECIFICATIONS: LUNDAY-THAGARD

TEST	ASTM METHOD	AASHTO METHOD	SPECS
SOFTENING POINT °F	D-36	T53	160-180
FLASH POINT COC °F	D-92	T48	575° F
PENETRATION @ 77°F,100g, 5s	D-5	T49	10-14
VISCOSITY @ (275°F) Cps	D-4402	T316	500-700 Cps
SOLUBILITY IN TCE, WT. %	D-2042	T44	99.0min.
SPECIFIC GRAVITY @ 60° F	D-70	T228	1.000-1.1000
API GRAVITY, 60°F	D-70	T228	---
DENSITY, 60°F, lbs/gallon	D-70	T228	---

AVAILABILITY: Upon Request

DOT SHIPPING NAME: UN3257,Elevated temperature,liquid,n,os,9,III

DOT PLACARD:Hot,3257