



9302 GARFIELD AVE • SOUTH GATE, CA 90280-3805



**PRODUCT SPECIFICATIONS**

**PRODUCT: LIQUID ASPHALT SLOW-CURING**

**GRADE: SC-3000**

**DATE: 12/10/2015**

**MEETS SPECIFICATIONS: ASTM 2026**

---

TESTS	ASTM METHOD	AASHTO METHOD	SPECS.
Viscosity, 135°C(275°F), cSt	D2170	T201	3000-6000
Flashpoint, C.O.C., °F	D92	T48	225 Min
API Gravity, 60°F	D287		
Density, 60°F, Lbs/Gallon	D287		
Water, vol. %	D95	T55	0.5 Max
Solubility in Trichloroethylene %	D2042	T44	99.0 Min
Distillation Test:	D402	T78	
Total Distillate to 500 °F,%	D402	T78	0.5 Max
Total Distillate to 680 °F,%	D402	T78	0-5
Viscosity of Residue 60°C(140°F), Cst	D2170	T201	4000-30000
Asphalt ResidueTest	D243	T56	
Residue of 100 Penetration, %	D5	T49	80Min
Ductility of 100 pen. Res., cm	D113	T51	100Min

**AVAILABILITY:** Readily available

**DOT SHIPPING NAME:** NA1999,Hot Asphalt,Cutback, 3,III

**DOT PLACARD:**Class 3,1999