



PRODUCT SPECIFICATIONS

PRODUCT: BUILT-UP ROOFING ASPHALT

GRADE: TYPE III

DATE: 12/10/2015

MEETS SPECIFICATIONS: LUNDAY-THAGARD

TEST	ASTM METHOD	AASHTO METHOD	SPECS
SOFTENING POINT °F	D-36	T53	185-205
FLASH POINT COC °F	D-92	T48	575° F
PENETRATION @ 77°F,100g, 5s	D-5	T49	15-30
PENETRATION @32°F,200g, 60s	D-5	T49	6 min.
PENETRATION @115°F,50g, 5s	D-5	T49	90 max.
DUCTILITY 77°F, 5cm/min,cm	D-113	T51	2.50min.
SOLUBILITY IN TCE, WT. %	D-2042	T44	99.0min.
SPECIFIC GRAVITY @ 60° F	D-70	T228	----
API GRAVITY, 60°F	D-70	T228	----
DENSITY, 60°F, lbs/gallon	D-70	T228	----
EVT @ 125 CPS ± 25°F (MOPP)	D-4402	T316	405±25° F
EVT @ 75 CPS ± 25°F (MECH)	D-4402	T316	445±25° F

AVAILABILITY: Readily available

DOT SHIPPING NAME: UN3257,Elevated temperature,liquid,n,os,9,III

DOT PLACARD:Hot,3257