



# WORLD OIL®

Your Premier Manufacturer of  
Roofing Asphalt Products



## Type III Bulk and Carton Asphalt

World Oil operates one of the largest carton roofing pouring facilities in the United States, manufacturing high quality Type 3 and Type 4 carton asphalt along with Type 3 bulk asphalt. We also produce a variety of roof coatings, windseals, and saturants used by our customers to manufacture roof shingles and other critical residential and industrial roof sealants. We are dedicated to supplying the best roofing products to local contractors, government agencies, and roofing manufacturers that provides you with comfort, convenience, and reliability.

With over 80 years of experience, World Oil is one of the few refineries in California. We are committed to our employees; the environment, safety, providing quality petroleum products, and exceptional customer service while earning the relationships of lifetime business partners.

Using dependable crude sources, and our ASSHTO accredited lab, we can ensure that the products leaving our facility consistently meet all ASTM D-312 specifications. Our asphalt products require less heat and cover more square footage than the competitors'. In addition, the less heat that is needed, the less energy that is used, resulting in more contractor savings and less risk to employee safety.

All published specifications are verified by third party laboratories.

### Required Type 3 ASTM D-312 Specifications

ASTM D-312 Test Method	Specifications		
D-36	Minimum	Maximum	
Softening Point	185°F	205°F	
D-92	Minimum		
Flashpoint (COC)	575°F		
D-5	32°F	77°F	115°F
Penetration @	6 min.	15-35	90 max.
D-113	2.5 min.		
Ductility @77°F, cm			
D-2042	99.4% min.		
Solubility, WT%			
D-4402	470°F max.		
Machine Spread EVT @ 75 CPS			
D-4402	430°F max.		
Hand Mop EVT @ 125 CPS			

### World Oil Type 3 Physical Characteristics

ASTM D-312 Test Method	Specifications		
D-36	Minimum	Maximum	Typical
Softening Point	194°F	200°F	198°F
D-92	Minimum	Typical	
Flashpoint (COC)	575°F	610°F	
D-5	32°F	77°F	115°F
Penetration @	19	25	39
D-113	2.5cm		
Ductility @77°F, cm			
D-2042	99.8%		
Solubility, WT%			
D-4402	430°F		
Machine Spread EVT @ 75 CPS			
D-4402	403°F		
Hand Mop EVT @ 125 CPS			

World Oil Refining  
P.O. Box 1519  
9302 Garfield Ave.  
South Gate, CA 90280  
orders@woildoilcorp.com

David Mora  
Roofing Asphalt Sales Manager  
Phone: (800)266-6551 Ext. 2219  
Cell: (562) 833-6308  
dmora@woildoilcorp.com